

Europäische Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 036 872 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
20.09.2000 Bulletin 2000/38

(51) Int Cl.7: D04H 1/46, D04H 3/10

(21) Application number: 00302155.7

(22) Date of filing: 16.03.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Kobayashi, Toshio, c/o Technical Center
Mitoyo-gun, Kagawa-ken 769-1602 (JP)
• Ishikawa, Hideyuki, c/o Technical Center
Mitoyo-gun, Kagawa-ken 769-1602 (JP)
• Mitsuno, Satoshi, c/o Technical Center
Mitoyo-gun, Kagawa-ken 769-1602 (JP)

(30) Priority: 18.03.1999 JP 7420699


(71) Applicant: UNI-CHARM CORPORATION
Kawanoe-shi Ehime-ken (JP)

(74) Representative: Parry, Christopher Stephen
Saunders & Dolleymore,
9 Rickmansworth Road
Watford, Herts. WD18 0JU (GB)

(54) Nonwoven fabric and process for making the same

(57) A nonwoven fabric 1 is formed with, in addition to crests 6 of high fibers' surface density and troughs 7 of low fibers' surface density extending in parallel one to another in one direction, bridge-like regions 8 each

extending transversely of this one direction between pair of the crest 6 and the trough 7 adjoining each other, and thereby enables a direction dependency of tensile strength and stretchability to be effectively alleviated.



EP 1 036 872 A1

Description

[0001] This invention relates to a nonwoven fabric and more particularly to a nonwoven fabric presenting no significant strength difference between in its machine direction (MD) and in its direction (CD) intersecting the machine direction and provided on its surface with a plurality of irregularities. This invention relates also to a process for making such a nonwoven fabric.

[0002] Japanese Patent Application Disclosure No. 1996-60509 describes a process for making a nonwoven fabric used as a wiper. According to this known process, a laminate consisting of a hydrophilic web and a hydrophobic web is continuously fed in one direction and the laminate is, as it is fed, subjected to high pressure water streams injected from fine orifice nozzles. In this manner, component fibers of the hydrophilic web and the hydrophobic web are rearranged and mechanically intertwined together to form a nonwoven fabric. This nonwoven fabric is then subjected to a heat treatment in order to crimp composite fibers contained in the web and thereby to form a plurality of irregularities on the surface of the nonwoven fabric. When this nonwoven fabric is used as a wiper, these irregularities formed in this manner function to scratch off dust and dirt from an object which should be cleaned.

[0003] As the nonwoven fabric obtained by subjecting the laminated web continuously fed in one direction to the high pressure columnar water streams, many of the component fibers lying immediately below the columnar water streams are forcibly moved aside. As a result, trough-like regions are defined by the component fibers of its surface density reduced by the moved aside fibers and crest-like regions are defined by the component fibers of its surface density increased by accumulated fibers. These trough- and crest-like regions extend in the web feed direction and are alternately arranged transversely of the web. Such a process is well known to those skilled in the art. It is also well known that such nonwoven fabric has a relatively high tensile strength and a relatively low stretchability in the MD but a relatively low tensile strength and a relatively high stretchability in the CD. In other words, the tensile strength as well as the stretchability of this nonwoven fabric largely depend on the direction. Accordingly, when it is desired to use this nonwoven fabric as the wiper, its orientation must be considered to avoid a possibility that the nonwoven fabric might be easily torn.

[0004] An object of this invention is to provide a nonwoven fabric requiring no consideration of its orientation to ensure the desired tensile strength as well as the desired stretchability and a process for making such a nonwoven fabric.

[0005] This invention aiming to achieve the object set forth above comprises a first invention relating to the nonwoven fabric and a second invention relating to the process for making this nonwoven fabric.

[0006] According to this first invention, there is provided a nonwoven fabric having first and second surfaces extending in parallel to each other and formed by component fibers mechanically entangled between the first and second surfaces, regions of high fibers surface density and regions of low fibers surface density continuously or intermittently extend in parallel one to another in one direction so as to be alternately arranged in a direction transversely of the one direction and to form undulations defined by crests corresponding to the regions of high fibers surface density and troughs corresponding to the regions of low fibers surface density; and

the nonwoven fabric further including bridge-like regions each extending transversely of the one direction between each pair of adjacent the region of high fibers surface density and the region of low fibers surface density and having a density higher than that in the region of low fibers surface density.

[0007] According to one embodiment of this first invention, the region of low fibers surface density has a width of 0.05 - 0.5 mm as measured transversely of the one direction.

[0008] According to another embodiment of this first invention, the component fibers partially extend transversely of the one direction.

[0009] According to still another embodiment of this first invention, the component fibers are short fibers or continuous fibers.

[0010] According to this second invention, there is provided a process for making a nonwoven fabric comprising the steps as follow:

a. a step of continuously feeding a fibrous web in one direction;

b. a step of feeding the fibrous web to a region lying immediately below high pressure columnar water streams injected from a plurality of nozzles arranged on a line extending transversely of the web at a range of feed rate deceleration of 16 ~ 35 % as defined by a formula:

Feed velocity deceleration (%) =

{(Feed velocity in front of columnar water streams) -

(Take-out velocity behind columnar water streams)} / (Take-out

velocity behind columnar water streams) x 100;

and

- 5 c. a step of taking-out the web having been treated by the columnar water streams in the one direction at the range of feed velocity deceleration.

10 **[0011]** According to one embodiment of this second invention, the columnar water streams are obliquely injected toward the web in the direction opposed to the web feed direction at an angle of $4 \sim 15^\circ$ with respect to a perpendicular line to the web.

[0012] According to another embodiment of this second invention, the fibrous web comprises short fibers or continuous fibers.

15 Fig. 1 is a perspective view of a nonwoven fabric according to this invention;
Fig. 2 is a sectional view taken along a line II-II in Fig. 1;
Fig. 3 is a sectional view taken along a line III-III in Fig. 1; and
Fig. 4 is a diagram schematically illustrating the steps of the process for making the nonwoven fabric.

20 **[0013]** Details of a nonwoven fabric according to this invention and a process for making the same will be more fully understood from the description given hereunder with reference to the accompanying drawings.

[0014] Fig. 1 is a perspective view of a nonwoven fabric according to this invention, Fig. 2 is a sectional view taken along a line II-II and Fig. 3 is a sectional view taken along a line III-III in Fig. 1. The nonwoven fabric 1 formed by mechanically entangled component fibers 2 is defined by its upper surface 3 which has significant irregularities and its lower surface 4 which is less irregular than the upper surface 3 i.e., rather smooth. The nonwoven fabric 1 includes 25 regions 6 of a high fibers surface density (high density regions) and regions 7 of a low fibers surface density (low density regions) which are alternately arranged in a direction as indicated by a double-headed arrow X and extend substantially in parallel one to another transversely of the direction X as indicated by a double-headed arrow Y. The nonwoven fabric 1 further includes bridge-like regions each extending in the direction as indicated by the double-headed arrow X between at least every pair of adjacent the regions 6, 7 and presenting a fibers surface density higher than that of the low density regions 7. The term "fibers surface density" used herein (referred to hereinafter simply as "surface density") means the number of component fibers present in a planar unit area as viewed from the upper surface 3 toward the lower surface 4 of the nonwoven fabric 1.

35 **[0015]** The component fibers 2 may be thermoplastic synthetic fibers, natural fibers such as pulp fibers, chemical fibers such as rayon fibers or a mixture of these fibers in a basis weight of $20 \sim 200 \text{ g/m}^2$. The synthetic fibers would preferably have a fineness of $0.1 \sim 3$ deniers and could be hydrophilicized if desired.

40 **[0016]** In the high density regions, the fibers 2 lying in the vicinity of the upper surface 3 are oriented substantially in the direction Y. The high density regions 6 include much more fibers 2 accumulated therein than in the low density regions 7 and correspondingly have a thickness larger than the low density regions 7. Accordingly, apices of the respective high density regions 6 lie at a level higher than apices of the low density regions 7. Each of the high density regions 6 preferably has a width of approximately $0.05 \sim 5 \text{ mm}$ as measured in the direction X and the maximum thickness of approximately $0.2 \sim 1 \text{ mm}$.

45 **[0017]** In the low density regions 7, the fibers 2 may be oriented substantially in the direction Y or not oriented in any particular direction. The low density regions 7 are not so crowded with the fibers 2 as the high density regions 6 and have the minimum thickness at their bottoms 11. Each of the low density regions 7 preferably has a width of approximately $0.02 \sim 0.5 \text{ mm}$ as measured in the direction X and a thickness of approximately $0.02 \sim 0.5 \text{ mm}$ as measured at its bottom 11. The high density regions 6 and the low density regions 7 are alternately arranged to form undulations in the direction X and thereby to define the crests and the troughs. The low density regions 7 have a tensile strength lower than that of the high tensile strength regions 6 and a stretchability higher than that of the high density regions 6 in the both directions X, Y.

50 **[0018]** Each of the bridge-like regions 8 extend in the direction X between each pair of the high density region 6 and the low density region 7 adjoining each other substantially at right angles or obliquely. An apex of the bridge-like region 8 lies at substantially the same level corresponding to or higher than the apex 9 of the high density region 6. However, it should be understood that the bridge-like region 8 may be lower than the apex 9 of the high density region 6 in the vicinity of opposite ends of the bridge-like region 8. While not specified, the bridge-like region 8 may be formed, for example, to have a width in the order of $0.5 \sim 1 \text{ mm}$, a length in the order of $5 \sim 100 \text{ mm}$ and a pitch in the order of $1 \sim 3 \text{ mm}$ at which the bridge-like region 8 are repeated in the direction Y. The component fibers 2 of the bridge-like region 8 may partially be oriented in the direction X. These fibers 2 extend between the bridge-like region 8 and the high density region 6 as well as between the bridge-like region 8 and the low density region 7 so that these regions 6,

7, 8 may be integrally connected together. Fibers surface density of the bridge-like region 8 may be similar to or higher than that of the low density region 7 and even higher than that of the high density region 6. When the nonwoven fabric 1 is observed as a whole, the bridge-like regions 8 appear as wrinkles formed on the upper surface 3 or on both the upper surface 3 and the lower surface 4 of the nonwoven fabric 1.

[0019] It is assumed that the nonwoven fabric 1 comprises the high density regions 6 and the low density regions 7 but none of the bridge-like regions as included in the nonwoven fabric of Fig. 1 as the important regions. Such nonwoven fabric will be easily stretched and torn particularly in the low density regions 7 as the nonwoven fabric is pulled in the direction X. On the other hand, if the nonwoven fabric is pulled in the direction Y, the presence of the high density regions 6 prevents the nonwoven fabric from being easily stretched and torn as it occurs when the nonwoven fabric is pulled in the direction X.

[0020] According to this invention, such nonwoven fabric having the strength and the stretchability largely depending on whether the nonwoven fabric is pulled in the direction X or in the direction Y, i.e., the remarkably direction-dependent nonwoven fabric is added with the bridge-like regions 8. The presence of these bridge-like regions function to reduce the stretchability and to improve the tensile strength of the low density regions 7. In this manner, the difference in the tensile strength as well as in the stretchability depending on whether the nonwoven fabric is pulled in the direction X or in the direction Y can be reduced and thus the homogeneous nonwoven fabric substantially free from the direction-dependency can be obtained.

[0021] When the nonwoven fabric 1 obtained in this manner is used as the wiper to wipe out dust and dirt, for example, from wall by scrubbing the wall in the direction Y, the bridge-like regions 8 can scrap off the dust and dirt from the wall. The thickness difference between the high density regions 6 and the low density regions 7 to define remarkable level difference serves also to scrap off the dust and dirt by scrubbing the wall with the nonwoven fabric 1 in the direction X. Furthermore, this nonwoven fabric 1 is homogeneous and therefore there is no remarkable difference in the tensile strength and the stretchability depending on whether the nonwoven fabric 1 is pulled in the direction X or in the direction Y. Accordingly, the user can scrub the wall without being nervous about an apprehensive rupture of the nonwoven fabric 1 by moving the nonwoven fabric 1 either in the direction X or in the direction Y.

[0022] If the component fibers 2 of the nonwoven fabric 1 are continuous fibers, an apprehension that the component fibers 2 of the nonwoven fabric 1 used as the wiper might partially fall off and these component fibers might stick again to the wall immediately after the dust and dirt have been wiped out from this wall. If the component fibers 2 are short fibers, on the other hand, a production rate can be improved with respect to the case in which the continuous fibers are used and a manufacturing cost of the nonwoven fabric 1 can be correspondingly reduced.

[0023] Fig. 4 is a diagram schematically illustrating a process for making the nonwoven fabric 1. Starting from the left hand in Fig. 4, a material web 100 is fed at a velocity v_1 from a comb or the like onto a drum-like support 102 rightward rotating. Thereupon, high pressure columnar water streams 103 are injected toward the web 100 from above. Specifically, the high pressure columnar water streams 103 are injected from a plurality of fine orifice nozzles 104 arranged above the drum-like support 102 on a line extending transversely of the web 100. These water streams rearrange the component fibers of the web 100 and entangle these component fibers to form a nonwoven fabric 101. The nonwoven fabric 101 is taken out at a velocity v_2 toward the right hand in Fig. 4 to be used as the nonwoven fabric 1 of Fig. 1. The transverse direction (i.e., CD) of this web 100 corresponds to the direction X of the nonwoven fabric 1 shown in Fig. 1 and the machine direction (i.e., MD) of the web 100 corresponds to the direction Y of the nonwoven fabric 1.

[0024] According to this process, the feed velocity v_1 is higher than the take-out velocity v_2 and these two velocities v_1 , v_2 are previously adjusted on the basis of the take-out velocity v_2 so that: a feed velocity deceleration $R(\%) = (v_1 - v_2)/v_2 \times 100$ may be maintained between 16 ~ 35 %. Position at which the array of nozzles 104 should be mounted is selected so that the nozzles 104 may inject the columnar water streams 103 obliquely from the front toward the web 100 supported on the drum 102 at an angle A of 4 ~ 15° with respect to a perpendicular line H to the web 100 as illustrated in Fig. 4.

[0025] Consequently, the web 100 is formed immediately ahead of the columnar water streams 103 with a plurality of wrinkles 106 extending transversely of the web 100. At the same time, these wrinkles 106 are fixed by the columnar water streams 103 on the web 100 substantially as they are formed. These fixed wrinkles 106 are destined to form the bridge-like regions 8 of the nonwoven fabric 1. As well known to those skilled in the art, on the regions of the web 100 travelling in one direction which are immediately subjected to the columnar water streams 103, many of the component fibers constituting the web 100 are forcibly moved aside so as to form the low density regions 7 of the nonwoven fabric 1. The component fibers forcibly moved aside are accumulated between each pair of adjacent columnar water streams so as to form the high density regions 6. According to the process illustrated by Fig. 4, there is provided a suction mechanism (not illustrated) within the drum 102 and the columnar water streams are rapidly absorbed by this suction mechanism after the columnar water streams have acted upon the web 100.

[0026] According to this invention, the columnar water streams 103 are injected toward the web 100 obliquely from the front and thereby not only a plurality of wrinkles 106 can be formed on the web 100 but also the component fibers

contained in the wrinkles 106 can be oriented transversely of the web 100. The bridge-like regions 8 obtained in this manner, distribute many fibers to the adjacent low density regions 7 and at least partially orient these fibers transversely of the web 100. In this manner, the tensile strength in the direction X of the nonwoven fabric 1 is improved and the stretchability in the direction X of the nonwoven fabric 1 is reduced.

Example 1

[0027] A web comprising continuous fibers of polypropylene having a fineness of 0.5 deniers and a basis weight of 30 g/m² was fed into the production line as illustrated by Fig. 4 and a wrinkled nonwoven fabric as shown by Fig. 1 was obtained under conditions as will be described below. This nonwoven fabric had a tensile strength per a basis weight of 1 g and a width of 1 cm as follows:

$$\text{Strength } S_{MD} \text{ in MD} = 36.7(\text{g/cm})/(\text{g/m}^2)$$

$$\text{Strength } S_{CD} \text{ in CD} = 27.3(\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD}/S_{MD} = 0.74$$

(Conditions for production)

[0028]

Injection angle of columnar water streams (A)	7.2°
Feed velocity deceleration (R)	33 %

Example 2

[0029] The nonwoven fabric obtained under the same conditions for production as Example 1 except that the columnar water streams injection angle (A) was adjusted to 10.1° had a tensile strength as follows:

$$S_{MD} = 33.0 (\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD} = 25.8 (\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD}/S_{MD} = 0.78$$

Comparative Example 1

[0030] The web similar to that used in Example 1 was fed into the production line as illustrated by Fig. 4 and a nonwoven fabric having no wrinkle was obtained under conditions as will be described below. This nonwoven fabric had a tensile strength as follows:

$$S_{MD} = 53.3(\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD} = 25.8(\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD}/S_{MD} = 0.48$$

(Conditions for production)

[0031]

Injection angle of columnar water streams (A)	0°
Feed velocity deceleration (R)	0 %

Comparative Example 2

[0032] A nonwoven fabric having no wrinkle was obtained under the conditions similar to those for Comparative Example 1 except that the columnar water streams were injected at an angle of 3.4° in the direction opposed to the web travelling direction. This nonwoven fabric had a tensile strength as follows:

$$S_{MD} = 47.8(\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD} = 24.2(\text{g/cm})/(\text{g/m}^2)$$

$$S_{CD}/S_{MD} = 0.51$$

[0033] Values of S_{CD}/S_{MD} obtained in Examples 1, 2 and Comparative Examples 1, 2, respectively, indicate that the differential strength between in the MD and in the CD direction is smaller for the nonwoven fabric of this invention than for the nonwoven fabric obtained in Comparative Examples.

[0034] As will be apparent from the foregoing description, the nonwoven fabric according to this invention includes, in addition to the regions of high fibers surface density and the regions of low fibers surface density extending in parallel to each other in one direction, the bridge-like regions extending transversely thereof. Such an unique arrangement is effective to reduce the differential tensile strength and stretchability of the nonwoven fabric possibly depending on whether the nonwoven fabric is pulled in the one direction or in the direction intersecting the one direction and thereby to make the nonwoven fabric homogeneous.

Claims

1. A nonwoven fabric having first and second surfaces and formed by component fibers mechanically entangled between said first and second surfaces, regions of high fibers surface density and regions of low fibers surface density continuously or intermittently extend in parallel one to another in one direction so as to be alternately arranged in a direction transversely of said one direction and to form undulations defined by crests corresponding to said regions of high fibers surface density and troughs corresponding to said regions of low fibers surface density; and
said nonwoven fabric further including bridge-like regions each extending transversely of said one direction between each pair of adjacent said region of high fibers surface density and said region of low fibers surface density and having a density higher than that in said region of low fibers surface density.
2. The nonwoven fabric according to Claim 1, wherein said region of low fibers surface density has a width of 0.05 ~ 0.5 mm as measured transversely of said one direction.
3. The nonwoven fabric according to Claim 1, wherein said component fibers partially extend transversely of said one direction.
4. The nonwoven fabric according to Claim 1, wherein said component fibers are short fibers or continuous fibers.
5. A process for making a nonwoven fabric comprising the steps of:
 - a. continuously feeding a fibrous web in one direction;
 - b. feeding said fibrous web to a region lying immediately below high pressure columnar water streams injected

EP 1 036 872 A1

from a plurality of nozzles arranged on a line extending transversely of said web at a range of feed rate deceleration of 16 ~ 35 % as defined by a formula:

Feed velocity deceleration (%) =

{(Feed velocity in front of columnar water streams) -

(Take-out velocity behind columnar water streams)} / (Take-out

velocity behind columnar water streams) x 100;

and

c. taking-out the web having been treated by said columnar water streams in said one direction at said range of feed velocity deceleration.

6. The process according to Claim 5, wherein said columnar water streams are obliquely injected toward said web in the direction opposed to the web feed direction at an angle of 4 ~ 15° with respect to a perpendicular line to said web.

7. The process according to Claim 5, wherein said fibrous web comprises short fibers or continuous fibers.




FIG.2




FIG.3





FIG. 4





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 2155

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 084 963 A (CHICOPEE) 3 August 1983 (1983-08-03) * page 3, line 8 - line 22 * * page 5, line 22 - line 24 * * page 6, line 19 - line 23 * * page 10, line 9 - line 20 * * claim 2; figures 1-7 *	1,3,4	D04H1/46 D04H3/10
X	EP 0 625 602 A (JOHNSON & JOHNSON INC) 23 November 1994 (1994-11-23) * page 4, line 22 - page 5, line 57 * * figures 1-11 *	1	
A		2	
X	EP 0 468 799 A (JOHNSON & JOHNSON) 29 January 1992 (1992-01-29) * page 3, line 30 - line 58 * * page 5, line 31 - page 6, line 39 * * page 9, line 38 - line 41 * * figures 1-12 *	1,4	
A		5-7	
X	EP 0 705 933 A (MCNEIL PPC INC) 10 April 1996 (1996-04-10) * column 7, line 51 - column 10, line 37 * * column 14, line 32 - line 45 * * column 15, line 33 - line 39; figures 1-17B *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) D04H
X	FR 2 209 003 A (JOHNSON & JOHNSON) 28 June 1974 (1974-06-28) * page 1, line 37 - page 2, line 30 * * page 5, line 1 - page 7, line 32 * * page 10, line 28 - page 11, line 21 * * claim 11; figures 1-18 *	1	
A		5-7	
P,X, D	EP 0 945 536 A (UNI CHARM CORP) 29 September 1999 (1999-09-29) * page 5, line 28 - line 54 * * figures 1-4 *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27 June 2000	Examiner Joly, F
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (Pct/C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 2155

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 3 688 355 A (OKZAKI MASAHIDE ET AL) 5 September 1972 (1972-09-05) * column 3, line 16 - line 38 * * column 5, line 12 - line 61 * * column 7, line 30 - line 34 * * claim 4; figures 1-10B *	5,7	
A	FR 2 601 970 A (VUILLAUME ANDRE) 29 January 1988 (1988-01-29) * page 2, line 36 - page 3, line 1 * * page 3, line 31 - line 34 * * page 7, line 7 - page 9, line 14 * * page 11, line 5 - line 18 * * figures 1-3 *	1,3-7	
A	FR 2 265 891 A (BERTIN & CIE) 24 October 1975 (1975-10-24) * page 3, line 26 - line 32 * * page 4, line 18 - page 6, line 2 * * figures 1-9 *	5,6	
A	US 4 276 681 A (MARSHALL PRESTON F) 7 July 1981 (1981-07-07) * column 2, line 51 - column 4, line 45 * * column 6, line 27 - line 30 * * figures 1-7 *	1,3-5,7	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Place of search	Date of completion of the search	Examiner	
THE HAGUE	27 June 2000	Joly, F	
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P/4C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 2155

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-06-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0084963 A	03-08-1983	AU 554230 B	14-08-1986
		AU 1068983 A	28-07-1983
		BR 8300259 A	25-10-1983
		CA 1189296 A	25-06-1985
		DE 3380992 D	25-01-1990
		IE 55306 B	01-08-1990
		IN 157924 A	26-07-1986
		MX 158696 A	27-02-1989
		NZ 202964 A	11-06-1986
		PH 18260 A	14-05-1985
		US 4612226 A	16-09-1986
		ZA 8300426 A	26-09-1984
EP 0625602 A	23-11-1994	AT 171736 T	15-10-1998
		AU 675296 B	30-01-1997
		AU 6073494 A	03-11-1994
		BR 9401639 A	01-11-1994
		CA 2122312 A	29-10-1994
		CN 1099969 A	15-03-1995
		CZ 9401017 A	16-11-1994
		DE 69413597 D	05-11-1998
		DE 69413597 T	04-03-1999
		ES 2122074 T	16-12-1998
		GR 1002552 B	28-01-1997
		HU 69420 A, B	28-09-1995
		JP 7138865 A	30-05-1995
		NO 941540 A	31-10-1994
		NZ 260419 A	24-04-1997
		PL 177334 B	29-10-1999
		US 5613963 A	25-03-1997
		ZA 9402979 A	30-10-1995
EP 0468799 A	29-01-1992	US 5238644 A	24-08-1993
		AT 132922 T	15-01-1996
		AU 647503 B	24-03-1994
		AU 8125591 A	30-01-1992
		BR 9103198 A	18-02-1992
		DE 69116253 D	22-02-1996
		DE 69116253 T	20-06-1996
		ES 2082144 T	16-03-1996
		GR 91100303 A, B	26-08-1992
		HK 121896 A	19-07-1996
		NZ 239090 A	25-11-1993
		US 5437904 A	01-08-1995
		US 5428876 A	04-07-1995
		ZA 9105862 A	31-03-1993

EPO FORM P0699

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 2155

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-06-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0705933 A	10-04-1996	US 5674587 A	07-10-1997
		CA 2158421 A	17-03-1996
		CN 1132276 A	02-10-1996
		FI 954357 A	17-03-1996
		JP 8176945 A	09-07-1996
		US 5822833 A	20-10-1998
		US 5906786 A	25-05-1999
FR 2209003 A	28-06-1974	NONE	
EP 0945536 A	29-09-1999	AU 1210499 A	05-08-1999
		CN 1233677 A	03-11-1999
		JP 11279915 A	12-10-1999
US 3688355 A	05-09-1972	JP 48023826 B	17-07-1973
		CA 938432 A	18-12-1973
		DE 2023139 A	19-11-1970
		FR 2042591 A	12-02-1971
		GB 1304603 A	24-01-1973
		NL 7006804 A	17-11-1970
FR 2601970 A	29-01-1988	NONE	
FR 2265891 A	24-10-1975	NONE	
US 4276681 A	07-07-1981	US 4228123 A	14-10-1980

EPO FORM P0489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82